

## Marten Texture Fine 652

**Description** Premium quality texture coat, based on acrylic copolymer emulsion resin, filled with selected aggregates and fine quartz.

### Principal uses

- For interior and exterior use.
- Good resistance to wet cleaning and scrubbing.
- Good weather resistance.
- Good hiding flexibility.
- Good adhesion properties.
- Can be used to create a variety of texture patterns.
- Almost odorless.
- Easy to apply.

### Characteristics

**Color** : White / or as per Martenson color card

**Specific gravity** : Approx. 1.82 g /cm<sup>3</sup>

**Volume solids (%)** : Approx. 56 %

**Theoretical coverage** : Approx. 1.5 – 2.0 kg/m<sup>2</sup>  
Depends upon substrate condition and method of application .

**Drying time** : Approx. 2 hours.

**Overcoat interval** : Min. 8 hours

**Shelf life** : 12 months from date of application  
(Stored in a dry and cool place)

### Surface preparation:

- New and previously painted surfaces should be dry and free from all loose and flaking materials, dirt, grease , wax, and similar contamination

### Paint systems advice

#### For new substrate:

- New concrete (plaster must be dry wait 3 to 5 weeks before application).
- All dirt , powder and other contamination must be removed
- Ensure cement based and plastered surfaces are dry and properly cleaned and
- Sufficiently dry max, 12% moisture.
- All dirt, powder and other contamination must be removed.
- Apply one coat of (610) Marten Masonry primer, or (611) Marten Acrylic sealer - Gypsum containing materials and substrate, which are powdery, should be
- primed with one coat of ( 612 ) Marten alkali resistant Primer .

#### For previously painted substrates:

- Remove all cracked, brittle and poorly adhering paint and any other contamination .
- Good intact wall paint layers must be cleaned with a 3 % solution of ammonia in Water.
- Glossy paint layers must be sanded properly.
- Not recommended on old Alkyd types of wall paint.

### Application guide line

#### Instrument for use

##### (Roller)

Volume of thinner : 0 – 5 %.

Recommended : pure water.

##### (Spray equipment)

##### Hopper gun

Volume of thinner : approx. 5 – 15 %

Recommended thinner : pure water.

**Cleaning Solvent** : pure water